

IN THE CLAIMS

Please amend the claims as follows:

Claim 1 (Currently Amended): A laser sintering powder comprising (a) at least one polyamide; (b) titanium dioxide particles, and (c) at least one flow aid which is a precipitated and/or fumed silica, wherein the at least one polyamide is nylon-6,12, nylon-11, nylon-12, or mixtures thereof.

Claims 2-3 (Canceled).

Claim 4 (Previously Presented): The sintering powder as claimed in claim 1, comprising from 0.01 to 30% by weight of titanium dioxide particles based on total amount of the at least one polyamide present in the powder.

Claim 5 (Previously Presented): The sintering powder as claimed in claim 4, comprising from 0.5 to 15% by weight of titanium dioxide particles based on the total amount of the at least one polyamide present in the powder.

Claim 6 (Previously Presented): The sintering powder as claimed in claim 1, comprising a mixture of titanium dioxide particles and particles of the at least one polyamide.

Claim 7 (Original): The sintering powder as claimed in claim 1, comprising titanium dioxide particles incorporated within polyamide particles.

Claim 8 (Original): The sintering powder as claimed in claim 1, wherein the titanium dioxide particles are anatase particles, rutile particles or a mixture of anatase and rutile particles.

Claim 9 (Currently Amended): The sintering powder as claimed in claim 1, further comprising at least one filler comprising glass particles.

Claims 10-11 (Canceled).

Claim 12 (Currently Amended): A process for preparing sintering powder as claimed in claim 1, comprising mixing at least one polyamide powder with said titanium dioxide particles and said at least one flow aid.

Claim 13 (Original): The process as claimed in claim 12, wherein mixing includes compounding the titanium dioxide particles into the polyamide powder.

Claim 14 (Previously Presented): A process for producing moldings comprising:
selectively laser-sintering a sintering powder comprising (a) at least one polyamide;
and (b) titanium dioxide particles, wherein the at least one polyamide is nylon-6,12, nylon-11, nylon-12, or mixtures thereof.

Claim 15 (Previously Presented): A molding produced by laser sintering a powder which comprises titanium dioxide and at least one polyamide having a median particle size of from 40 to 250 μm , wherein the at least one polyamide is nylon-6,12, nylon-11, nylon-12, or mixtures thereof.

Claims 16-17 (Canceled).

Claim 18 (Original): The molding as claimed in claim 15, wherein the powder comprises from 0.01 to 30% by weight of titanium dioxide particles, based on the total amount of the polyamide present in the powder.

Claim 19 (Original): The molding as claimed in claim 18, wherein the powder comprises from 0.5 to 15% by weight of titanium dioxide particles based on the total amount of the polyamide present in the powder.

Claim 20 (Original): The molding as claimed in claim 15, wherein the titanium dioxide particles are anatase particles, rutile particles, or a mixture thereof.

Claim 21 (Original): The molding as claimed in claim 15, further comprising one or more fillers.

Claim 22 (Previously Presented): The molding as claimed in claim 21, wherein the one or more fillers are glass particles.

Claim 23 (Previously Presented): A method of lowering sensitivity to thermal stress in a molding comprising at least one polyamide, the method comprising adding titanium dioxide to at least one polyamide powder in an amount sufficient to reduce the thermal sensitivity of a molding produced by laser sintering.

Claim 24 (Previously Presented): The laser sintering powder as claimed in claim 1, wherein the at least one polyamide has a median particle size of from 40 to 250 μm .

Application No. 10/685,525
Reply to Final Office Action mailed March 16, 2006

Claim 25 (Canceled).